

## L-61032 Polyethylene Glycol(600) Diacrylate

CAS#26570-48-9

### Description

L-61032 is a high boiling point, water soluble difunctional acrylate monomer with long chain skeleton, it has good flexibility after curing, and low viscosity, low skin irritation, chemical resistance, excellent flexibility, softness, low shrinkage, good adhesion and water solubility.

### Technical data

Appearance	Transparent liquid
Color number (APHA)	≤100
Viscosity (25°C, CPS)	80-120
Water(%)	≤0.2
Polymerization inhibitor (ppm)	400-600
Refractive index	1.469
Surface tension (dyne/cm)	42.3
Tg (°C)	-41
Functional group	2

### Performance

High water solubility, good flexibility, fast curing speed.

### Applications

Synthetic resins, inks, adhesives, printing varnishes, paints, etc.

### Storage

To prevent the product from polymerization and gelling, please keep it sealed and away from heat and light. Recommended storage temperature is not higher than 30°C. Unused products must be sealed and stored in a timely manner and cannot be stored in the open. Safe storage time is 6 months at room temperature( 25°C) and under ventilation. 25KG/200KG/barrel

**Tips: L-61032 it has high flexibility, low odor, low shrinkage, water solubility.**

Note: Technical data represents typical values only. In view of the differences in formulas, production process, conditions, all the above statements must be adjusted according to the actual situation, our company does not make any promises. Our company reserves the right to reform its products without prior notice of any changes.